




CN-2V 200AH 铅酸蓄电池



技术参数

额定电压	容量 (10hr, 1.80V/单体, 25°C)	重量	最大 放电电流	最大 充电电流	自放电 (25°C)	推荐使用温度	壳体材料
2V	200Ah	12.5Kg	30I ₁₀ A(3min)	≤0.25C ₁₀	≤3%/月	15°C~25°C	ABS工程塑料
使用温度范围	充电电压 (25°C)	充电方式 (25°C)		循环寿命	温度对容量的影响		
放电: -45°C~50°C	浮充: 2.25V-2.3V	浮充使用: 2.275±0.025V		100%DOD 572 times	105% @ 40°C		
充电: -20°C~45°C	均充: 2.35V-2.4V	温度参数: ±3mV/°C		50%DOD 1422 times	90% @ 0°C		
储存: -30°C~40°C		循环使用: 2.45±0.05V		30%DOD 2218 times	70% @ -20°C		
		温度参数: ±5mV/°C					

特点

阀控密封胶体蓄电池, 是采用当代先进技术研制开发的新型高能蓄电池。在正常使用时无游离电解液, 无酸雾溢出, 维护使用方便, 可广泛用于太阳能、风能、电信通讯系统、不间断电源 (UPS) 等领域。该产品设计浮充使用寿命达6年以上。

不同终止电压、放电时间的放电电流 (安培, 25°C)


F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	4h	5h	8h	10h
1.60V	378	320	302	231	159	128	77.2	56.4	45.5	38.3	26.4	21.7
1.65V	333	294	284	213	152	122	75.2	55.2	44.5	37.6	26.0	21.4
1.70V	320	277	271	196	143	115	72.4	53.6	43.6	37.1	25.6	21.0
1.75V	305	263	257	182	136	111	70.0	52.0	42.4	36.0	25.2	20.6
1.80V	293	249	242	173	127	104	66.8	50.4	40.8	35.2	24.5	20.0
1.85V	260	221	215	157	115	93.6	60.4	47.6	39.0	33.6	23.8	19.4

认证


ISO9001
CE
符合的标准:
GB/T 22473-2008
GB/T 19638.2-2005
YD/T799-2002
IEC61427-2005
GB/T 19001-2016 idt ISO 9001:2015
EN IEC 61000-6-2:2019, EN IEC 61000-6-4:2019
EN IEC 61000-3-2:2019+Al:2021
EN 61000-3-3:2013+Al:2019




充电特性




放电特性 (25°C)




温度与寿命



放电特性



放电深度与循环次数



温度与容量

