



CN-2V 500AH 铅酸蓄电池



技术参数

额定电压	容量 (10hr, 1.80V/单体, 25°C)	重量	最大 放电电流	最大 充电电流	自放电 (25°C)	推荐使用温度	壳体材料
2V	500Ah	29Kg	30I ₁₀ A(3min)	≤0.25C ₁₀	≤3%/月	15°C~25°C	ABS工程塑料
使用温度范围	充电电压 (25°C)	充电方式 (25°C)		循环寿命	温度对容量的影响		
放电: -45°C~50°C	浮充: 2.25V-2.3V	浮充使用: 2.275±0.025V		100%DOD 572 times	105% @ 40°C		
充电: -20°C~45°C	均充: 2.35V-2.4V	温度参数: ±3mV/°C		50%DOD 1422 times	90% @ 0°C		
储存: -30°C~40°C		循环使用: 2.45±0.05V		30%DOD 2218 times	70% @ -20°C		
		温度参数: ±5mV/°C					

特点

阀控密封胶体蓄电池, 是采用当代先进技术研制开发的新型高能蓄电池。在正常使用时无游离电解液, 无酸雾溢出, 维护使用方便, 可广泛用于太阳能、风能、电信通讯系统、不间断电源 (UPS) 等领域。该产品设计浮充使用寿命达6年以上。

不同终止电压、放电时间的放电电流 (安培, 25°C)


F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	4h	5h	8h	10h
1.60V	859	727	687	525	398	320	193	141	114	95.8	65.9	54.2
1.65V	758	668	646	485	381	305	188	138	111	94.0	65.0	53.4
1.70V	727	630	616	444	357	288	181	134	109	92.7	63.9	52.6
1.75V	693	598	584	414	341	277	175	130	106	90.1	63.1	51.4
1.80V	667	567	550	394	317	259	167	126	102	88.0	61.3	50.0
1.85V	590	502	488	357	287	234	151	119	97.5	84.0	59.4	48.5

认证


ISO9001
CE
符合的标准:
GB/T 22473-2008
GB/T 19638.2-2005
YD/T799-2002
IEC61427-2005
GB/T 19001-2016 idt ISO 9001:2015
EN IEC 61000-6-2:2019, EN IEC 61000-6-4:2019
EN IEC 61000-3-2:2019+Al:2021
EN 61000-3-3:2013+Al:2019




充电特性




放电特性 (25°C)




温度与寿命



放电特性



放电深度与循环次数



温度与容量

